

hi METOLOSE 抹特乐素

Additive for Tile setting, Internal plastering, External rendering, Machine-Spraying based on cement / gypsum / lime.

建築用高性能混和剤

Excellent Workability
High Water Retention
Economical Effect
Rapidly Solubility

施工性優 高保水性 経済性佳 速溶解性










Shin-Etsu Chemical Co., Ltd.

Cellulose Department Asahi-Tokai Building

6-1, Ohtemachi 2-chome, Chiyoda-ku, Tokyo, Japan TEL: 81-3-3246-5261 FAX: 81-3-3246-5372

How To Use 使用方法



Mix hiMETOLOSE with other materials as dry powder. 将hiMETOLOSE与其他材料混合



再加水充分合拌



Add water and knead well. Get a high-quality mortar. 可得高品质的砂浆

Characteristics

材料特点

Excellent solubility



Dissolves rapidly in cement and other alkaline materials.

在水泥或其他碱性材料中可快速溶解

Improvement of workability



Improves trowelling workability due to ball-bearing effects caused by entrained air.

因空气连行产生滚珠轴承效果,可改善镘涂的作业性


Improvement of water retention



Controls "Dry-out" caused by water absorption into the background and evaporation due to high water retention.

由于高保水性,抑制水份被底材吸收及向大气蒸发而使 砂浆干燥

Economical effects



Increase sand / cement ratio of mortar becouse of excellent workabillity

Furthermore the air volume in mortar increse by about 10%, thus material cost can be redused. 由于高作业性,可提高砂/水泥比率,尤其可提高大约 10%的砂浆空气量,因而降低材料费用。

Dosage

Application	Dosage of hiMETOLOSE	用途	hiMETOLOSE标准用量
Thin coating mortar	2-4 pack per 50kg cement	水泥粉光	1袋水泥 (50kg)配2-4袋
Thick coating mortar	1-2 pack per 50kg cement	砂浆打底	1袋水泥 (50kg)配1-2袋
Punp-up mortar	1/2-1 pack per 50kg cement	喷 浆 用	1袋水泥 (50kg)配1/2-1袋
Gypsum plaster	1/4-1/2 pack per 20kg gypsum plaster	石膏粉光	1袋粉光 (20kg)配1/4-1/2袋
Tile mortar	2-4 pack per 50kg cement	磁砖粘贴	1袋水泥 (50kg)配2-4袋

Precaution in handling

Spilled powder becames slippyery when wet. Therefore, please clear the area with a dry broom or dry floor cloth.

In the case of eye or mouth contact, please wash well with water.

注意事项

本产品遇水沾湿容易滑,溢出散落于地上时用干的扫帚或 干布清除干净,本品不慎眼睛或嘴巴沾到了,请同大量水 来冲洗请用大量水来冲洗。